

DESCRIPTION

Super Fix is a single component, cement based adhesive for ceramic tiles, slate, porcelain, pavers and natural stone.

Super Fix is a grey or off-white powder, consisting of graded sand, cement, synthetic resins and additives, specifically formulated to achieve superior bond strengths to most materials normally used in building.

Super Fix is suitable for internal and external, wall and floor applications, including bathrooms, kitchens, garages and driveways. It is suitable for use in fully submerged environments, such as fountains.

CLASSIFICATION IN ACCORDANCE TO AS4992.1-2006

Super Fix is an improved cement based adhesive with extended open time, classified as C2E.

FEATURES AND BENEFITS

- Single component system, requires only the addition of clean water.
- Extended open time.
- Quick and easy to apply.
- Excellent adhesion to floor and rigid wall substrates.
- Suitable for thin and thick bed applications.
- Suitable for heavy traffic load areas.
- Can be further improved with the addition of *ACS NeoLastic*.

RECOMMENDATIONS

Do **not** use:

- On wooden, PVC, rubber, linoleum, metal or painted substrates;

- For the installation of moisture sensitive stone or agglomerates.
- In swimming pools unless it is mixed with *ACS NeoLastic* or *ACS NeoLastic* diluted 1:1 with water.
- Contact ACS Technical Services for information on tiling over other surfaces not mentioned in this data sheet.

APPLICATION

Substrate Preparation

All substrates must be dry, flat, solid, structurally sound, free of loose particles, paint, grease, oil, wax, dust and any contamination which may inhibit or prevent adhesion.

Cementitious substrates, such as concrete, screeds and renders must not be subject to shrinkage after the installation of tiles. Therefore, they must be fully cured in accordance with the provisions of AS3958.1-2007 and it is essential that they are free of laitance and release agents. Steel trowelled concrete should be mechanically abraded to provide a key.

Fibre cement sheet substrates must be fixed in accordance to the manufacturer's instructions and the relevant Australian Standards.

Highly absorbent substrates should be primed with *ACS NeoLastic* diluted 2:1 with water.

Substrates which have become hot due to exposure to sunlight may be cooled down with water.

Masonry substrates should be prepared with a cementitious render to ensure a smooth, sound substrate is achieved.

Mixing

Pour approximately 4.8 – 5.6 litres of clean, cold water into a clean container and slowly add 20 kg of *Super Fix* while slowly mixing with a low speed mixer. Mix thoroughly to a smooth, homogeneous consistency. Allow the mix to stand for approximately five minutes and then stir again briefly. The adhesive is now ready for use.

Mixed this way, the adhesive has a pot life of approximately four hours.

Note: The characteristics of *Super Fix* can be improved by mixing it with *NeoLastic* or *NeoLastic* diluted 1:1 with water. The characteristics improve in order to exceed the requirements of C2S2 and C2S1 respectively.

Use approximately 6.0 – 6.8 litres of *NeoLastic* per 20 kg of *Super Fix* or approximately 5.6 – 6.2 litres of *ACLastic* diluted 1:1 with water per 20 kg of *Super Fix*.

Applying the Adhesive

Apply *Super Fix* onto the substrate using a notched trowel. Choose a notched trowel of an appropriate size to achieve a coverage as recommended by AS 3958.1 – 2007 or better.

To maximize adhesion, spread a thin layer of the adhesive onto the substrate. Immediately thereafter, build up the required thickness using the notched side of the trowel.

For external applications, areas subject to vehicular traffic or point loads, also spread the adhesive onto the back of the tile (back-butter) in order to achieve full coverage and to eliminate any voids under the tiles.

Do not spread more adhesive than can be covered with tiles within the adhesive's open time.

Where possible, spread adhesive so as to leave horizontal ribs on walls and unidirectional ribs on floors.

Discard any material that has exceeded the pot life or working time of the product.

Installing the Tiles

Press tiles firmly into freshly notched adhesive within the open time and move the tile at least the width of a rib perpendicular to the adhesive ribs. Adjust tiles as necessary within 45 minutes of installation.

The open time of *Super Fix* is approximately 30 minutes under normal temperature and humidity conditions. Unfavourable conditions, such as high temperature, wind, sunlight or highly absorbent substrates may drastically shorten this time, sometimes to as little as a few minutes. It is therefore necessary to repeatedly check whether a skin has formed on the adhesive. If a skin has formed the adhesive should be re-trowelled or discarded.

Tiling installed with *Super Fix* must not be subjected to rain or washout for at least 24 hours after installation, and should be protected from direct sunlight for 36 hours. Remove any adhesive from the face of tiles with a damp cloth while the adhesive is still fresh.

Movement Joints

It is essential that movement joints are carried through the tile and the adhesive and are kept free from dust, adhesive and other contaminants.

Refer to AS3958.1 - 2007 for guidance on design and construction of movement joints.

CLEAN UP

Clean all tools and equipment with water before the adhesive dries.

GROUTING

Allow 24 hours drying time before grouting with an appropriate ACS Grout.

OPEN TO TRAFFIC

Floors are ready to receive light foot traffic after approximately 24 hours and may be put into full use after approximately seven days.

CONSUMPTION

Approximately 1.2kg per m² per mm of adhesive thickness.

A 20kg bag should cover 5-6 m² depending on the size of the notched trowel and evenness of the substrate.

PACKAGING

Super Fix is available in 20kg paper bags.

STORAGE

Stored in original, unopened packaging, in cool dry conditions, *ACS Super Fix* will keep for 6 - 12 months. Storing in areas of high humidity or excess moisture may affect the contents and shorten shelf-life.

TECHNICAL DATA

DRY PRODUCT

Form:	grey powder
Bulk Density:	1500 kg/m ³
Mixing ratio/20kg bag	4.8 – 5.6 litres

The following typical results were obtained at 23 ±2 °C with 50% R. H.

MIXED PRODUCT

Consistency:	Homogeneous Paste
Wet Density:	1500 kg/m ³
pH:	10 – 12
Pot life:	4.0 – 6.0 hours
Open Time :	15 – 20 minutes
Setting time:	3 – 4 hours
Drying Time:	24 hours

TENSILE ADHESION STRENGTHS

28 days cure	> 1 N/mm ²
Water immersion	> 1 N/mm ²
Heat ageing	> 1 N/mm ²
Freeze / Thaw	> 1 N/mm ²
20 min open time	> 1 N/mm ²
30 min open time	> 0.5 N/mm ²

HANDLING

Use only in well ventilated areas. Wear protective clothing to minimise skin contact. The use of P1 Masks, tight fitting goggles and barrier creams is recommended.

SAFETY

Super Fix contains cement, which can be irritating to the skin and eyes. During use, avoid inhalation of dust and contact with the skin and eyes. Wear suitable clothing, gloves, eye protection and respiratory protective equipment.

If contact with the skin occurs, thoroughly clean the area with plenty of fresh water and soap. In case of contact with the eyes rinse with plenty of fresh water and seek medical advice. If swallowed, seek medical attention immediately – **Do not** induce vomiting.

For further information consult the **Material Safety Data Sheet** and read the product label carefully before use. **Material Safety Data Sheets** are available by phoning **1800 077 744**.

Please Note:- The information given in this data sheet is based on our current knowledge of the product when properly stored, handled and applied. We cannot guarantee that the product will be suitable, effective or safe when used for any purpose other than its stated uses.

To the extent that it is lawful, we exclude warranties implied by law and limit our liability to the cost of replacing the product. We accept no responsibility for loss or injury caused by improper use, incompetent preparation, inexperienced or negligent application, or ordinary wear and tear.

Service or advice given by our staff should not amount to responsibility for the project - since the owner, or their contractor (and not River Sands), is responsible for procedures relating to the application of the product.



Applied Concrete Solutions
A Division of River Sands Pty Ltd
683 Beenleigh Redland Bay Rd,
Carbrook Qld 4130
Ph: 07 3287 6444 Fax: 07 3287 6445
Sydney: (02) 9756 1711
Melb: (03) 9311 9225
Perth: 0423 023 164
Toll Free Helpline: 1800 077 744
www.appliedconcretesolutions.com.au